

TIXO 3H A+B (TRECOSIL RTV)
2-Part Moulding Rubber

Introduction

TIXO 3H A+B is a two component room temperature condensation curing silicone compound.

The cured product is a hard rubber with high mechanical properties and good shelf-life stability. It is an excellent rubber for mould-making of intricate patterns on vertical surfaces, skin moulding and applications demanding an extremely tough rubber on vertical surfaces.

Key Features

- Fast cure
- No inhibition
- High tear strength
- Dimensional stability
- Application on vertical surfaces
- Good chemical resistance to resins (PE-PU-Epoxy)

Use and Cure Information

The curing process starts as soon as the catalyst is added. Under normal conditions of temperature and humidity, typical curing characteristics are described below. Once cured, if the product is to be used in contact with aggressive chemicals, such as high styrene polyester resins or epoxies, it is recommended that the rubber be allowed to cure for 24 hours before use.

How to Use

Charge 100 parts by weight of Tixo 3H A and 5 parts by weight of Tixo 3H B into a suitable plastic or metal container. Mix thoroughly. After 15-30 seconds of mixing, the product will become thixotropic. Continue to mix until the colour contrast between the base (beige) and the catalyst (green) disappears in order to achieve homogeneity.

Once mix is finished the product can be applied on the model using a brush or a spatula

Property

Test Method

Value

Uncured Product

Colour:		Beige/Green
Appearance:		Viscous liquid
Viscosity:	Brookfield	< 50000 mPa.s
catylased viscosity	Brookfield	paste
Pot Life:		> 45 minutes *
De-mould time		> 18 hours *
* measured at 23+/-2°C and 65% relative humidity.		

Cured Elastomer

(after 7 days cure at 23+/-2°C and 65% relative humidity)

Tensile Strength:	BS903 Part A2	3.50 MPa
Elongation at Break:	BS903 Part A2	300 %
Tear Strength:	BS903 Part A3	14 kN/m
Hardness:	ASTM D 2240-95	25 ° Shore A
Specific Gravity:	BS 903 Part A1	1.36
Linear Shrinkage:		0.35 %
Coefficient of Thermal Expansion:		
Volumetric Linear		714 ppm / °C
		238 ppm / °C
Min. Service Temperature:		-40 °C
Max. Service Temperature:	AFS 1540B	180 °C

All values are typical and should not be accepted as a specification.

Health and Safety - Material Safety Data Sheets available on request.

Packages –Kits of 5.25 kg, 21 kg and 210 kg

Storage and Shelf Life – Expected to be 12 months for the part A and 9 months for the part B in original, unopened containers below 35°C.

Revision Date: 12.04.07

The information and recommendations in this publication are to the best of our knowledge reliable. However nothing herein is to be construed as a warranty or representation. Users should make their own tests to determine the applicability of such information or the suitability of any products for their own particular purposes. Statements concerning the use of the products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is to be assumed.