



MAL Magyar Aluminium  
MAL Hungarian Aluminium  
MAL Ungarische Aluminium



Levél cím/Address/Adresse: H-8401 AJKA, Pf. 124. HUNGARY

Tel.: +36 (88) 522-400 Fax.: +36 (88) 311-634

www.mal.hu e-mail: mal@mal.hu timfold@mal.hu

Trading Center: H-1012 Budapest, Logodí u. 34/B. HUNGARY

Tel.: +36 (1) 309-4200 Fax.: +36 (1) 309-4211

www.mal.hu e-mail: mal@mal.hu timfold@mal.hu

## ALUMINIUM HYDROXIDE

### GROUND TYPE

Type of product		ALOLT 30AF
Al(OH) <sub>3</sub> *	%	min. 99.5
SiO <sub>2</sub>	%	max. 0.01
Fe <sub>2</sub> O <sub>3</sub>	%	max. 0.01
Na <sub>2</sub> O <sub>total</sub>	%	max. 0.3
Moisture	%	max. 0.5
Bulk density	kg/m <sup>3</sup>	max. 700
Average particle size d <sub>50</sub>	µm	5 - 10
Whiteness	%	min. 93

\* By difference

Valid from: 14. 06. 2007