



RAYMOND GROUP s.r.o.

Jasenice 1593

755 01 Vsetín

Czech Republic

Registered in OR in Ostrava, division C, folder 21220

INo: 2584251, VAT: CZ25842251, DUNS: 49 - 537 - 7751

TECHNICAL DATA SHEET

| | | | |
|--|---|---|-----------------|
| Product designation: T 160 | | Fabric type: Glassfibre made of yarn | |
| Data sheets No.: 05 | | Approved and valid from: 03.01.2005 | |
| Works standart: 16002 | | Valid until: | |
| Technical parametres: | | | |
| 1. Surface mass: | g / m ² | 160 ± 11% | DIN EN 12127 |
| 2. Used material: | tex | | DIN EN 12654 |
| Warp | | EC 9 68 | |
| Weft | | EC 9 68 | |
| 3. Density: | l cm | | DIN 53853 |
| Warp | | 12,0 ± 0,5 | |
| Weft | | 11,5 ± 0,5 | |
| 4. Weave: | | TWILL 2/2 | |
| 5. Thread sizing: | | SILANE | |
| 6. Edges: | | CUT | |
| 7. Loss on ignition: | % of surface mass, max | 99,6 | EN 61067 - 2 |
| 8. Thickness: | mm, average | 0,2 | EN ISO 5084 |
| 9. Tensile strenght: | N / 5 cm, average | | EN ISO 13934 -1 |
| Warp | | 1433,7 | |
| Weft | | 1543,9 | |
| 10. Width: | cm | ± 0,5 | DIN EN 1773 |
| 11. Roll length: | m | ± 0,5 | DIN EN 1773 |
| 12. Packing: | Fabric wound on 76 mm tubes, rolls delivered wrapped in foil, fasted on wooden palletes. | | |
| 13. Storing: | Clean and dry place, temperatures between - 10° and 50° C, preventing any pressure to the rolls from the outside. | | |
| 14. Other data: | Other data, sampling method, testing and quality checking are mentioned in 16002 works standard. | | |
| Processed by: | | Approved by: | |
| Vojtech Sacher Weaving mill manager | | Radomir Ovcacik Director | |

tel.: +420 571 448 705, fax.: +420 571 448 707 www.raymondgroup.cz info@raymondgroup.cz